

Flex-, thin- and flow-bed mortar

CODEX POWER RX 6 TURBO

Quick setting, flexible thin- and flow-bed mortar

APPLICATIONS

Quick setting, flexible thin and flow-bed mortar with variably adjustable consistency for the installation of all types of ceramic tiles as well as thin natural stone floor coverings insensitive to discolouration. The variably adjustable consistency makes the installation in thin and flow-bed process possible, especially with large size tiles and slabs. codex RX 6 Turbo meets the requirements according to EN 12 004 C2 FT S1. Unevennesses in the installation substrate can be compensated up to 10 mm in one coat. For interior and exterior use on walls and floors in residential, commercial and industrial buildings.

LEED: Meets the LEED requirements in IEQ Credit (4.1) Low Emitting Materials (LEED v4)

SUITABLE FOR

- ▶ Large size tiles and plates
- ▶ Fine and coarse ceramic tiles and slabs
- ▶ Earthenware, stoneware, fine stoneware
- ▶ Natural stone covering and concrete slabs resistant to deformation and discolouration
- ▶ Glass and porcelain tiles with rough backing
- ▶ Compound-suitable insulation and light building boards

SUITABLE ON

- ▶ Gypsum carton and gypsum fibreboard panels
- ▶ Cement, lime cement and gypsum plaster
- ▶ Walls from brick, concrete blocks, gas concrete, lime sand brick
- ▶ Tile carrier elements
- ▶ Site-mixed concrete, prefab concrete elements (at least 6 months old)
- ▶ Calcium sulphate and cementitious screeds
- ▶ Compound-capable dry construction elements
- ▶ Gritted mastic asphalt
- ▶ Heated floor constructions
- ▶ UZIN Multimoll plates



PRODUCT BENEFITS/FEATURES

- ▶ Ready for foot traffic and jointing after approx. 2.5 hours
- ▶ Excellent wetting
- ▶ Top application reliability
- ▶ Up to 10 mm mortar bed thickness
- ▶ Smooth and easy to process
- ▶ Extreme early strength
- ▶ For interior and exterior use

TECHNICAL SPECIFICATIONS

Pack type	paper bag
Pack size	25 kg
Shelf life	6 months
Color	dark grey
Minimum working temperature	+ 5 °C to + 25 °C
Ideal working temperatures	+ 10 °C to + 25 °C
Water quantity required	0.28 - 0.35 litres/ kg 7 - 8 litres/ 25 kg
Working Time/ Pot Life	approx. 45 minutes*
Working time	approx. 20 minutes*
Set to foot traffic	after approx. 2,5 hours*
Ready for jointing	after approx. 2,5 hours*
Resilient	after approx. 48 hours*
Final strength	after approx. 28 days*
Consumption	1.5 - 3.0 kg/m ²

*At 23 °C and 50% rel. humidity.



SUBSTRATE PREPARATION

The substrate must be sound, dry, flat, free of cracks, clean, load-bearing and free of materials that could impair adhesion strength.

Test the substrate in accordance with applicable standards or bulletins and report any deficiencies. Mechanically prepare smooth concrete surfaces, adhesion-reducing or weak layers and clean dust-free, if necessary. Prepare according to type and properties with suitable primers and levelling compounds from the codex range of products. Prime gypsum-based substrates.

Calcium sulphate flowing screeds must be ground, vacuumed and primed. Allow primers to always dry completely. Heated screeds must be treated according to "Interface coordination for heated floor constructions" (heat drying, heating to accelerate readiness for covering).

When installing large size tiles and plate coverings (from 60 cm edge length and/or tile size over 0.2 m²) on substrates sensitive to moisture such as calcium sulphate screeds, they must be pretreated with a codex protective or barrier primer.

Refer to the product data sheets for other codex products used.

APPLICATION

1. Provide cold water, cast in powder while stirring vigorously and mix to a homogeneous mortar. Mix well again briefly after a short maturing time. Note pot life.
2. Using a smoothing trowel, spread a thin, continuous contact layer onto the substrate, top up with fresh mortar and comb evenly with a notched trowel. A largely full-surface bed is achieved by choosing the suitable tooth profile and application technique (e.g. buttering / floating).
3. Before the skin starts to form, push the tiles into the adhesive bed with a slight twisting motion and press down.
4. Do not stir or mix material that has already set with water or powder. Clean tools and soiled ceramics with water while fresh.
5. Joint floor covering only after sufficient setting and drying of the installation mortar.

COVERAGE

Notch size	Approx. consumption
4 mm, C1	1.5 kg/m ²
6 mm, C2	2.0 kg/m ²
8 mm, C4	2.6 kg/m ²
10 mm, C5	3.0 kg/m ²

IMPORTANT NOTES

- ▶ Store in a cool and dry place. Carefully and tightly re-seal opened packaging and use the contents quickly.

- ▶ Optimum processing at + 15 to + 25 °C, relative humidity 75%. Cold and high humidity will delay whilst heat and low humidity will accelerate the working, setting and drying time.
- ▶ Drying and strength development depend on the weather conditions. Weather cycles ensuring sufficient setting and drying of the coverings must be taken into account with exterior use; appropriate protective measures must otherwise be taken.
- ▶ Protect newly installed areas from drafts, direct sunlight and heat as well as wetness.
- ▶ For high application thicknesses (over 5 mm) on moisture-sensitive substrates such as calcium sulphate screeds, a suitable codex barrier primer should be used.
- ▶ For the installation of large-format tiles and slabs, the relevant data sheets and technical information of the "Fachverbandes Fliesen und Naturstein" in the ZdB e.V. (Association for Tiles and Natural Stone) as well as the applicable standards and regulations must be observed. Obtain technical application advice if necessary.
- ▶ Use codex products according to the current product overview for areas with increased exposure to chemicals and acids as well as on wood or chipboard panels, metal and plastics or solicit application consulting.
- ▶ Floor temperature control through radiator connection lines returns must be equipped with a temperature limiter (< 38 °C).
- ▶ Always apply proper codex composite seal for external applications. Glazed vitrified tiles are a preferred covering material. Obtain application consulting for dust-pressed vitrified tiles.
- ▶ The following apply as well, amongst others, or are recommended for special consideration:
 - DIN 18 352 "Tile and slab work"
 - DIN 18 157 "Ceramic work in thin bed processes"
 - ZDB bulletins:
 - "Coverings on cementitious screed – heated"
 - "Coverings on cementitious screed – unheated"
 - "Coverings on calcium sulphate heated screed"
 - "Exterior coverings"
 - "Interface coordination"
 - BEB bulletin:
 - "Assessment and preparation of substrates"

SEALS OF QUALITY & ECOLABELS

- ▶ Low chromate content acc. Regulation (EC) No. 1907/2006 (REACH)
- ▶ EMICODE EC 1 PLUS / Very low-emission

CONSTITUENTS

Special cements, mineral aggregates, redispersible polymers and additives.

PROTECTION OF THE WORKPLACE AND ENVIRONMENT

Contains cement low in chromate acc. Regulation (EC) No. 1907/ 2006 (REACH). Cement produces strong alkaline on reaction with water. Avoid contact with skin and eyes. In the event of contact, rinse immediately with water. In the event of skin or eye irritation, seek medical advice. Use protective gloves. When mixing wear a protective dust-mask. Presents no physiological or ecological risk when fully cured.

DISPOSAL

Where possible, collect product residues and re-use. Do not allow to get into drains, sewers or ground. Empty paper packaging is recyclable. Collect waste product, mix with water, allow to harden, then dispose as Construction Waste.